

# MICROMAX<sup>®</sup>

Added durability for the toughest environments

## MicroMax<sup>®</sup> Applications

Dirt, Oil and Grease

Hazardous Dry Particulate

Non-hazardous Liquids




Serged Seam



### MicroMax<sup>®</sup> Features:

- Rip-stop nylon scrim adds strength and durability
- Liquid under pressure will not pass through fabric
- Ideal for Isocyanate paint
- Proven protection for Pesticide Spraying

### MicroMax<sup>®</sup> Configurations



**Coverall TG412**

- Zipper closure
- Sizes: S – 5X  
Case Pack: 25



**Coverall TG414**

- Zipper closure
  - Attached hood
  - Boots
- Elastic wrists  
Sizes: S – 5X  
Case Pack: 25



**Coverall TG417**

- Zipper closure
  - Elastic wrists
  - Elastic ankles
- Sizes: S – 5X  
Case Pack: 25



**Coverall TG428**

- Zipper closure
  - Attached hood
  - Elastic wrists
  - Elastic ankles
- Sizes: S – 5X  
Case Pack: 25

### MicroMax<sup>®</sup> Physical Properties

Physical Property	Test Method	Units	Test Results
Basis Weight	ASTM D3776	oz/y <sup>2</sup>	2.10 oz/y <sup>2</sup>
Grab Tensile MD	ASTM D5034	lbs.	32.4 lbs.
Grab Tensile XD	ASTM D5034	lbs.	32.6 lbs.
Trapezoidal Tear MD	ASTM D5733	lbs.	5.1 lbs.
Trapezoidal Tear CD	ASTM D5733	lbs.	6.2 lbs.
Surface Resistance	EN1149	Ω	Pass

### MicroMax<sup>®</sup> ASTM F903 Penetration Data

Chemical Tested	Concentration %	Test Time – Minutes	Test Results
Diazinon (Roundup)	100%	60	Pass
Motor Oil-40 wt.	100%	60	Pass
Bleach-household	100%	60	Pass
Isocyanate Based Paint	100%	60	Pass
Sodium Hydroxide	50%	60	Pass
Sodium Hypochlorite	10%	60	Pass
Blood	Challenge Fluid Liter – 3.20 x 108 (PFU/mL)	Assay Results PFU/mL <1	Pass